

060

791336

RESPONSIBLE OFFICER *[Signature]*
S. L. 6. 81

T = element present; but concentration too low to measure
X = element concentration is below detection limit
= element not determined

TUBE No.	SAMPLE No.	Cu	Pb	Zn	Ag	Fe (%)			
1	KR7636	135	10	30	0.5	3.25			
2	37	125	20	35	X	2.60			
3	38	415	20	50	X	4.80			
4	39	160	X	25	0.5	1.90			
5	40	65	X	20	X	0.91			
6	41	215	5	30	X	1.95			
7	42	150	X	70	X	2.80			
8	43	140	X	60	0.5	2.05			
9	44	75	X	50	X	3.15			
10	45	35	X	40	0.5	3.05			
11	46	5	X	30	X	2.05			
12	47	5	X	45	X	3.80			
13	48	20	X	45	X	3.85			
14	49	115	X	60	0.5	4.43			
15	50	200	5	55	X	5.00			
16	51	105	X	35	X	2.40			
17	52	80	X	35	X	1.85			
18	53	65	5	40	0.5	3.65			
19	54	170	X	20	X	1.40			
20	KR7655	35	X	25	X	1.50			
21	56	30	X	25	X	1.75			
22	57	385	X	45	X	2.35			
23	58	355	X	110	X	4.85			
24	59	145	X	35	X	1.65			
25	60	25	X	30	0.5	3.75			
26	61	15	X	15	X	3.25			
27	62	10	10	15	X	2.20			
28	63	5	X	15	X	2.80			
29	64	30	X	40	0.5	3.50			
30	65	200	X	45	0.5	4.05			
31	66	90	X	35	X	2.50			
32	67	115	X	55	X	4.20			
33	68	135	20	30	0.5	2.15			
34	69	150	X	65	X	1.45			
35	70	25	10	15	0.5	1.35			
36	71	80	15	30	0.5	1.60			
37	72	65	5	10	X	0.92			
38	73	75	5	15	X	1.15			
39	74	15	10	10	0.5	0.41			
40	KRY675	110	10	20	X	0.67			
Detection		5	5	5	0.5	5			
Standard	ASS 5	425	325	100	0.9				
Repeat -	KR7636	135	X	30	X	3.10			
Repeat -	KR7655	40	X	30	0.5	1.45			
Method		A1/1							

Cont No: 83.1 08 236
69