

069

791337

B. Dore  
S. 1. 6 1. 84

RESPONSIBLE OFFICER

T = element present; but concentration too low to measure  
X = element concentration is below detection limit  
- = element not determined

Tube No.	SAMPLE No.	Cu	Pb	Zn	Ag	Fe (%)	
1	KR 7676	40	20	15	x	0.92	
2	77	30	x	10	x	0.41	
3	78	10	x	10	x	1.90	
4	79	45	5	10	x	1.05	
5	80	130	15	10	x	2.20	
6	81	15	x	10	x	0.30	
7	82	115	x	10	x	1.00	
8	83	130	x	10	x	1.85	
9	84	40	5	10	x	0.74	
10	85	155	10	10	x	0.47	
11	86	175	15	10	x	1.60	
12	87	65	x	15	x	1.60	
13	88	210	x	15	x	1.15	
14	89	185	x	20	x	1.85	
15	90	100	x	30	x	2.05	
16	91	50	x	15	0.5	0.29	
17	92	145	15	25	0.5	0.81	
18	93	30	5	50	x	0.85	
19	94	25	55	585	0.5	3.15	
20	KR 7695	5	65	230	x	0.94	
21	96	135	115	145	0.5	0.32	
22	97	65	60	40	0.5	0.32	
23	98	35	50	30	0.5	0.34	
24	99	265	45	25	0.5	0.20	
25	KR 7700	35	15	20	0.5	0.21	
26	01	190	15	20	x	0.18	
27	02	120	5	25	0.5	0.19	
28	03	180	x	25	0.5	0.18	
29	04	15	10	15	x	0.12	
30	05	145	x	25	0.5	0.62	
31	06	60	x	65	0.5	1.40	
32	07	30	x	50	0.5	0.84	
33	08	25	x	15	0.5	0.26	
34	09	260	x	20	x	0.26	
35	10	290	5	75	x	1.55	
36	11	170	5	40	0.5	0.91	
37	12	185	x	50	0.5	1.40	
38	13	120	x	65	x	1.60	
39	A	110	x	65	0.5	1.65	
40	KR 7715	80	x	40	0.5	0.98	
Detection		5	5	5	0.5	5	
Standard	ASS5	460	330	110	0.5	22.0	
Repeat-	KR 7676	40	25	10	0.5	0.90	
Repeat-	KR 7695	5	75	220	0.5	0.94	
Method		A1/1					

Core No. 53-1 0.8-236  
V9