

RESULT SHEET

Order No. _____

070

791338

RESPONSIBLE OFFICER *B. Dora*
 9. 1. 6. 1. 81

Results in ppm unless otherwise specified
 T = element present; but concentration too low to measure
 X = element concentration is below detection limit
 - = element not determined

TUBE No.	SAMPLE No.		Cu	Pb	Zn	Ag	Fe (%)		
1	KR	7716	5	x	25	0.5	1.20		
2		17	5	5	20	x	1.20		
3		18	30	x	25	x	1.00		
4		19	15	30	25	0.5	1.30		
5		20	20	10	45	x	2.55		
6		21	5	x	15	x	1.65		
7		22	x	x	15	0.5	1.85		
8		23	10	5	15	x	1.25		
9		24	5	5	10	x	2.50		
10		25	x	x	10	x	2.50		
11		26	10	15	20	x	2.40		
12		27	5	5	40	x	2.85		
13		28	x	5	15	0.5	2.60		
14		29	x	x	20	0.5	3.10		
15		30	x	x	35	x	2.40		
16		31	5	x	30	x	1.50		
17		32	x	x	130	x	4.30		
18		33	x	x	30	x	1.90		
19		34	385	170	65	1.0	2.15		
20	KR	7735	1650	150	50	1.5	3.00		
21		36	35	x	20	x	2.00		
22		37	65	10	40	0.5	1.80		
23		38	5	5	20	x	3.15		
24		39	5	20	20	0.5	3.10		
25		40	40	15	15	0.5	2.15		
26		41	5	10	15	x	2.65		
27		42	15	x	20	0.5	2.75		
28		43	20	x	30	0.5	2.00		
29		44	55	x	55	0.5	2.65		
30		45	35	x	105	x	3.55		
31		46	40	x	60	0.5	2.05		
32		47	90	x	110	0.5	4.00		
33		48	105	x	75	0.5	2.85		
34		49	10	x	120	0.5	5.05		
35		50	20	x	110	0.5	4.05		
36		51	130	x	80	x	3.20		
37		52	10	x	70	0.5	2.85		
38		53	5	x	20	0.5	1.00		
39		54	25	x	35	0.5	1.65		
40	KR	7755	20	x	25	0.5	1.15		
Detection			5	5	5	0.5	5		
Standard	AS65		460	315	105	0.5	24.0		
Repeat-	KR	7716	5	x	25	0.5	1.25		
Repeat-	KR	7735	1700	160	50	2.0	3.05		
Method			AI/1						

Code No: 83-1-98-236
19