

071

791339

15 *Storan*
9 / 6 / 81

RESPONSIBLE OFFICER

T = element present; but concentration too low to measure
X = element concentration is below detection limit
- = element not determined.

TUBE No.	SAMPLE No.		Cu	Pb	Zn	Ag	Fe (1/2)		
1	KR	7756	20	X	20	0.5	0.83		
2		57	15	X	20	1.0	1.00		
3		58	15	X	15	0.5	1.60		
4		59	30	X	20	1.0	1.20		
5		60	25	X	15	0.5	1.40		
6		61	30	X	25	1.0	1.00		
7		62	35	X	15	1.0	0.78		
8		63	5	X	10	0.5	2.05		
9		64	5	X	10	1.0	2.60		
10		65	X	X	25	X	1.40		
11		66	X	X	25	0.5	1.05		
12		67	5	X	50	0.5	2.50		
13		68	10	X	35	0.5	1.60		
14		69	10	X	45	1.0	1.30		
15		70	40	X	20	0.5	0.48		
16		71	110	10	20	1.0	0.32		
17		72	35	X	25	X	0.66		
18		73	50	S	20	0.5	0.49		
19		74	20	S	20	X	0.36		
20	KR	7775	15	X	15	X	0.59		
21		76	5	X	15	0.5	1.70		
22		77	15	X	15	0.5	2.80		
23		78	5	X	20	0.5	1.60		
24	KR	7779	15	X	15	X	1.85		
25									
26									
27									
28									
29									
30									
31									
32									
33									
34									
35									
36									
37									
38									
39									
40									
Detection			5	5	5	0.5	5		
Standard	ASSE		430	320	100	0.5	250		
Repeat -	KR	7756	20	X	20	X	0.85		
Repeat -	KR	7775	15	X	15	X	0.62		
Method			AI/1						

Core No: 53.1 08-236
Number of