

# RESULT SHEET

Order No. KP 2599

132

791400

TUBE No.	SAMPLE No.		Cu	Pb	Zn	Ag	Fe	Mn		
1	TS	10502	5	55	170	1.0	1.25%	110		
2		04	x	5	625	0.5	3.15%	540		
3		06	20	40	285	0.5	2.45%	500		
4		07	x	5	15	1.0	1550	10		
5		08	x	x	45	0.5	3550	20		
6		09	35	245	180	2.5	5950	40		
7		10	5	70	245	1.0	1.1%	35		
8		11	x	15	40	0.5	3150	10		
9		12	10	105	1550	1.0	2200	10		
10		13	x	5	85	1.0	3800	10		
11		14	10	200	350	0.5	3950	15		
12		15	x	10	170	2.0	2700	5		
13		16	15	20	120	0.5	2100	15		
14		17	x	20	30	1.0	2650	5		
15		18	x	15	45	0.5	1100	5		
16		19	x	15	35	0.5	3350	10		
17		20	5	65	295	1.0	4200	15		
18		21	5	65	280	1.0	3900	10		
19	TS	10522	x	25	35	0.5	2200	x		
20										
21										
22										
23										
24										
25										
26										
27										
28										
29										
30										
31										
32										
33										
34										
35										
36										
37										
38										
39										
40										
Detection			5	5	5	0.5	5	5		
Standard	ASS 5		445	325	125	0.5	21.0%	245		
Repeat-	TS	10502	5	55	170	0.5	1.25%	110		
Repeat-										
Method										

CODE No: 83-1.08 109

RESPONSIBLE OFFICER B. Khan  
9 / 4 / 81

T = element present; but concentration too low to measure  
 X = element concentration is below detection limit  
 - = element not determined