

173
791441

RESULT SHEET

Page No. _____
Order No. KP2592

TUBE No.	SAMPLE No.		Cu	Pb	Zn	Ag	Fe	Mn		
1	TS	10569	5	10	85	0.5	4600	10		
2		70	x	5	30	0.5	3650	10		
3		71	x	x	25	1.0	3550	10		
4		72	65	20	105	0.5	1.7%	110		
5		73	10	5	110	0.5	1.0%	45		
6		74	55	5	700	1.0	2.2%	65		
7		75	15	40	200	0.5	2800	x		
8		76	5	x	20	1.0	2100	x		
9		77	10	60	730	0.5	1.9%	1000		
10		78	5	5	75	1.5	4450	15		
11		79	5	10	55	1.5	4400	5		
12		80	10	5	80	1.0	3650	10		
13		81	5	5	60	1.0	4550	10		
14		82	5	5	40	1.0	3450	5		
15		83	5	5	60	1.0	9000	15		
16		84	10	55	110	0.5	4200	25		
17		85	5	40	60	x	1550	5		
18		88	5	10	110	0.5	1350	5		
19		89	20	50	110	0.5	800	x		
20	TS	10590	5	5	65	0.5	2100	x		
21		91	x	x	55	0.5	1950	x		
22		92	x	x	30	1.5	1400	x		
23		93	x	x	40	0.5	1000	x		
24		94	x	x	35	0.5	800	x		
25		95	x	x	25	x	600	x		
26		96	20	20	15	x	1250	x		
27		98	x	10	110	x	1500	5		
28		99	x	5	40	x	1300	x		
29	TS	10600	x	x	30	0.5	1100	x		
30		01	10	35	55	x	3700	10		
31		02	5	10	25	0.5	1600	x		
32		03	x	x	25	x	1100	x		
33		04	x	10	25	0.5	800	x		
34		05	40	215	280	x	1.3%	x		
35		06	5	30	50	x	1150	x		
36		07	5	20	125	x	1300	x		
37		08	x	35	140	x	1050	5		
38		09	5	100	510	x	4850	15		
39		10	5	15	200	x	1.2%	40		
40	TS	10611	x	5	50	0.5	2650	10		
Detection			5	5	5	0.5	5	5		
Standard	ASSS		455	320	135	0.5	20.8%	230		
Repeat-	TS	10569	5	5	95	0.5	4450	10		
Repeat-	TS	10590	5	5	60	0.5	2300	x		

83-103-097
 Core No.

RESPONSIBLE OFFICER B. D. D.
6, 4, 81

results in ppm unless otherwise specified
 T = element present; but concentration too low to measure
 X = element concentration is below detection limit
 - = element not determined