

RESULT SHEET

Order No. KP 2512

TUBE No.	SAMPLE No.	Cu	Pb	Zn	Ag	Fe	Mn		
1	TS 10654	x	30	55	x	8200	330		
2	55	x	x	45	x	2650	90		
3	56	x	x	45	x	1600	45		
4	58	S	50	150	x	5700	40		0.91
5	59	x	x	50	0.5	4300	35		
6	60	S	110	240	x	1.1%	40		0.8
7	61	x	10	65	x	1.2%	45		
8	62	x	5	65	x	8750	35		
9	67	x	25	100	x	7350	20		0.3 - 1
10	70	x	10	85	x	1.1%	350		
11	71	x	x	80	x	7150	30		
12	72	S	x	75	x	7050	35		
13	74	x	20	60	x	2650	5		
14	75	10	40	165	x	1650	10		
15	76	x	20	180	x	5100	30		
16	77	x	50	300	x	3100	5		
17	78	S	40	190	x	4800	40		
18	80	x	5	75	x	3050	5		
19	81	x	5	90	x	3250	5		
20	TS 10682	x	x	55	x	4300	5		
21	83	x	25	60	0.5	5000	20		
22	84	x	5	45	x	4900	10		
23	85	x	10	130	0.5	1.75%	330		
24	86	x	35	250	0.5	6450	160		
25	87	15	240	1850	0.5	1.6%	530		
26	88	S	25	155	x	1.4%	195		
27	89	S	10	55	0.5	4000	20		
28	90	S	10	75	x	5600	20		
29	92	15	30	60	0.5	8200	20		
30	93	5	10	80	1.5	7900	35		
31	94	20	25	35	0.5	5100	20		
32	95	15	15	35	0.5	5050	20		
33	96	70	20	115	x	2.5%	140		
34	97	25	10	70	0.5	1.5%	125		
35	98	10	5	45	0.5	1.05%	130		
36	99	5	20	40	1.5	1.0%	130		
37	TS 10700	15	105	130	1.0	9600	125		
38	01	5	20	75	1.0	8700	130		
39	02	10	70	60	1.0	9750	125		
40	TS 10703	10	10	55	1.0	1.75%	140		
Detection		S	S	S	0.5	S	S		
Standard	ASSS	470	340	140	1.0	21.0%	220		
Repeat -	TS 10654	x	25	55	x	7900	345		
Repeat -	TS 10682	S	S	55	x	4200	S		

RESPONSIBLE OFFICER 12.10.2011
6.1.4.81

sent; but concentration too low to measure
concentration is below detection limit
element not determined

791443

Code No. 43-1-081