

178

# RESULT SHEET

Order No. KP 2598

791446

TUBE No.	SAMPLE No.		Cu	Pb	Zn	Ag	Fe	Mn		
1	TS	10751	x	x	50	0.5	3750	55		
2		52	x	5	50	0.5	5550	75		
3		53	15	5	140	x	2.6%	560		
4		54	5	x	70	0.5	1.0%	185		
5		55	x	x	40	x	5200	60		
6		56	x	x	45	x	1850	25		
7		57	x	155	25	0.5	1850	50		
8		58	5	20	125	1.0	2.0%	470		
9		59	x	x	50	0.5	8800	100		100
10		60	x	x	50	0.5	1850	40		
11		61	x	x	20	0.5	2200	45		05
12		62	x	x	20	0.5	2000	10		
13		63	x	x	30	0.5	3900	5		
14		64	10	200	305	1.0	8100	5		
15		65	x	15	125	1.0	7750	20		
16		66	x	10	195	1.0	2.25%	110		
17		67	x	10	270	0.5	1350	10		
18		68	x	5	65	2.0	1450	70		
19		69	5	20	155	0.5	1.9%	135		
20	TS	10770	20	20	95	0.5	1.15%	30		
21		71	20	15	90	0.5	1.05%	30		
22		72	10	15	75	0.5	1.2%	60		
23		73	20	60	150	0.5	4000	10		
24		74	x	x	15	x	1300	x		
25		75	x	x	20	0.5	1450	x		
26		76	x	x	50	x	1700	x		
27		77	1200	x	120	x	8950	30		
28		78	15	x	30	x	1200	x		
29		79	10	x	20	0.5	8600	20		
30		80	10	5	315	x	1950	20		
31		81	20	5	370	x	2950	120		
32		82	5	40	60	x	1100	10		
33		83	x	x	30	x	2100	15		
34	TS	10784	5	5	90	x	2100	25		
35	TS	10964	x	25	250	0.5	1200	x		
36		65	x	5	880	x	1300	x		
37		66	x	x	40	1.5	1050	x		
38		67	x	5	40	1.5	740	x		
39		68	5	5	100	0.5	970	x		
40	TS	10969	x	5	30	0.5	760	x		
Detection			5	5	5	0.5	5	5		
Standard	ASS 5		430	290	130	x	21%	225		
Repeat -	TS	10751	x	x	40	0.5	3700	50		
Repeat -	TS	10770	20	15	95	x	1.2%	35		

Code No 83-100

RESPONSIBLE OFFICER *13 Khan*  
9 4 81

= element present; but concentration too low to measure  
x = element concentration is below detection limit  
- = element not determined