

Results in ppm unless otherwise specified
 T = element present, but concentration too low to measure
 X = element concentration is below detection limit
 - = element not determined

RESPONSIBLE OFFICER

B. Blum
 21 / 3 / 81

791512

244

TUBE No.	SAMPLE No.		Cu	Pb	Zn	Ag	Fe			
1	TS	8435	20	15	95	X	1550			
2		36	X	X	20	X	910			
3		37	5	X	30	X	830			
4		38	X	X	50	X	510			
5		39	30	X	80	X	860			
6		40	5	10	120	X	1350			
7		41	X	X	65	X	1150			
8		42	5	X	140	X	960			
9		43	5	10	115	0.5	830			
10		44	5	25	85	X	780			0.71
11		45	5	15	95	0.5	570			0.8
12		46	5	5	45	X	660			0.3+1
13		47	10	50	65	0.5	560			
14		48	X	X	45	X	750			
15		49	X	X	150	0.5	640			
16		50	15	5	150	0.5	1350			
17	TS	10051	5	X	175	X	1250			
18		52	5	25	295	0.5	1200			
19		53	X	X	145	X	580			
20		54	X	X	145	0.5	420			
21		55	5	30	135	1.5	530			
22		56	5	X	140	X	460			
23		57	X	X	90	0.5	590			
24		58	10	25	140	0.5	2750			
25		59	X	X	65	X	1600			
26		60	X	X	30	0.5	1150			
27		61	X	X	40	X	1350			
28		62	X	X	40	X	1000			
29		63	X	X	45	X	1000			
30		64	X	X	50	X	890			
31		65	X	X	60	X	560			
32		66	X	15	355	0.5	600			
33		67	X	X	95	X	450			
34		68	X	X	60	X	580			
35		69	X	X	60	X	660			
36		70	X	X	115	0.5	480			
37		71	X	10	105	X	430			
38		72	X	10	50	X	650			
39		73	X	10	60	X	660			
40	TS	10074	X	X	65	X	760			
Detection			5	5	5	0.5	5			
Standard	ACSS		445	310	130	X	20.0%			
Repeat -	TS	8435	15	15	85	X	1450			
Repeat -	TS	10054	X	5	160	X	400			
Method			ALL							

Code No. 83+1