

## APPENDIX 6

## TABLE 11

## EL20/80 LAUNCESTON

WEIGHTED AVERAGE AIR DRIED BASIS  
SEAM QUALITY  
(Using RD and Seam Split Reserves)  
50 ASH DRY BASIS CUT OFF

SEAM	SPECIFIC ENERGY MJ/Kg	RD gm/cc	ASH %	SULPHUR %	INHERENT MOISTURE %	RESERVE STATUS
LAO	13.95	1.56	27.88	0.23	17.65	Inferred II
LBO	12.42	1.59	32.45	0.24	18.08	
PB1*	12.17	1.5	31.4	0.2	22.2	N/C
PB2*	12.72	1.51	28.3	0.11	22.1	N/C
PCO	12.33	1.58	33.23	0.22	18.61	II
PD1*	12.35	1.48	28.4	0.19	25.2	II
SAO*	12.29	1.56	31.1	0.28	19.8	N/C
SCO*	11.22	1.65	27.5	0.26	16.4	N/C
SDO*	13.1	1.62	33.3	0.24	13.6	N/C

\* Analysis available from only one cored hole

II Indicated Class II Reserves  
N/C Not calculated as Reserves