

771053

056

TENEMENT CODE	
RECORD CODE	TYPE
1 0 0 0	
TEST DATE	LAB
0180382	BR
RESULT BASIS	AD

THIESS BROS. PTY. LIMITED — MINING DIVISION

PROJECT NAME	TENEMENT No.	AREA
TASMANIA	EL 20/80	ROSEVALE

LAB TEST REQUEST No.
LAB TESTER/CHECKER
AUTHORISING INITIALS
SHEET

P. Ellis

LAB TEST REQUEST No.	1811
LAB TESTER/CHECKER	EE
AUTHORISING INITIALS	
SHEET	010

COAL ANALYSIS TEST SHEET No. 1

TP 816

LABORATORY SAMPLE NUMBER	FIELD SAMPLE NUMBER	BOREHOLE NUMBER	SEAM NAME	TYPE	BASE DEPTH	THICKNESS	SIZE CODE	FRACTION	RD	SIZE/FLOAT YIELD %	PROXIMATE ANALYSIS % BY WEIGHT				C S N	SPECIFIC ENERGY	TOTAL SULPHUR % WT	COMPOSITE SAMPLES	CONTIN
											INHERENT MOISTURE	VOLATILE MATTER	ASH	FIXED CARBON					
60245	G 2635	C0022			886	036		RAW		22.1	7.9	16.8	71.7	3.6		284	0.11	-	
46	36				920	034				19.0	9.6	23.6	56.0	10.8		684	0.23	-	
47	38				945	036				17.8	7.4	30.2	42.7	19.7		1190	0.28	-	
48	39				1077	082				16.2	20.1	26.3	37.2	16.4		1050	0.23	-	
49	40				1137	060				16.6	10.6	32.6	36.4	20.4		1360	0.20	-	
50	42				1220	051				16.4	20.1	25.5	41.0	13.4		884	0.21	-	
51	44				1332	074				14.3	25.0	30.4	23.0	21.6		1384	0.19	-	
52	45				1412	080				15.2	24.3	28.0	30.1	17.6		1190	0.18	-	
53	46				1501	089				16.8	9.6	35.3	32.3	22.8		1538	0.26	-	
54	48				1617	097				15.7	23.7	25.5	37.3	13.5		952	0.19	-	
55	49				1676	089				16.4	18.9	26.5	39.2	15.4		1042	0.22	-	
56	51				1788	063				17.6	17.3	21.5	48.1	13.1		764	0.18	-	
57	52				1831	043				25.0	3.2	11.2	84.3	1.3		910	0.05	-	
58	53				1900	080				23.4			82.0					-	
59	54				1959	059				24.2	4.4	12.9	81.0	1.7		1100	0.06	-	
60	55				2027	068				16.3	21.4	24.0	41.0	13.6		896	0.20	-	
61	56				2100	073				19.2	14.7	19.0	59.3	7.0		482	0.12	-	
62	57				2174	074				19.4	13.0	21.4	59.7	5.9		532	0.15	-	
63	58				2281	107				15.4	24.1	25.7	36.2	14.0		944	0.27	-	
64	60				2372	051				14.7	21.9	31.9	23.8	22.4		1500	0.28	-	