

771055

058

TENEMENT CODE			
RECORD CODE		TYPE	
1	0	0	
TEST DATE		LAB	
08/03/80		RBR	
RESULT BASIS		A,D	

THIESS BROS. PTY. LIMITED — MINING DIVISION

PROJECT NAME TASMANIA	TENEMENT No. EL 20/80	AREA ROSEVALE
--------------------------	--------------------------	------------------

LAB TEST REQUEST No.
LAB TESTER/CHECKER
AUTHORISING INITIALS
SHEET

5013
AC
3 of 10

COAL ANALYSIS TEST SHEET No. 1

TP 816

LABORATORY SAMPLE NUMBER	FIELD SAMPLE NUMBER	BOREHOLE NUMBER	SEAM NAME	TYPE	BASE DEPTH	THICKNESS	SIZE CODE	FRACTION	RD	SIZE/FLOAT YIELD %	PROXIMATE ANALYSIS % BY WEIGHT				C S N	SPECIFIC ENERGY	TOTAL SULPHUR % WT	COMPOSITE SAMPLES	CONTIN
											INHERENT MOISTURE	VOLATILE MATTER	ASH	FIXED CARBON					
A60285	C 2688	C0032			38.1	0.93		RAW		16A	26.4	19.0	47.5	7.1	526	0.15			
86	89				38.7	0.30				209	11.5	16.4	68.6	3.5	288	0.08			
87	90				40.46	1.33				165	28.6	19.4	47.7	4.3	558	0.10			
88	92				40.79	0.33				16A	20.3	24.8	42.2	12.7	966	0.16			
89	94				41.84	0.62				172	9.1	34.7	36.3	19.9	1408	0.17			
90	96				42.61	0.59				177	11.4	26.5	46.4	15.7	1030	0.13			
91	98				43.87	0.25				170	14.5	26.9	39.8	18.8	1172	0.11			
92	99				44.49	0.56				159	27.6	20.1	42.0	10.3	714	0.07			
93	2702				45.29	0.57				157	15.1	28.2	37.9	18.8	1222	0.13			
94	03				46.19	0.52				179	18.7	18.0	56.2	7.1	464	0.07			
95	05				47.33	0.52				183	20.4	14.3	61.3	4.0	276	0.05			
96	06				49.53	1.22				218	11.4	12.8	74.1	11.7	068	0.03			
97	07				87.2	0.55				156	25.3	24.1	37.1	13.5	962	0.25			
98	2710	C0033			9.36	0.16				144	18.2	32.4	25.9	23.5	1516	0.17			
99	11				10.32	0.42				171	21.0	20.5	46.8	11.7	734	0.10			
60300	13				12.25	0.41				154	21.8	29.1	31.5	17.6	1198	0.13			
01	15				12.94	0.40				157	18.5	30.7	30.8	20.0	1346	0.15			
02	17				13.66	0.44				151	22.1	29.2	28.3	20.4	1272	0.11			
03	18				14.63	0.97				208	7.4	19.6	63.3	9.7	602	0.09			
04	19				23.87	0.61				221			74.3						