

771061

064

TENEMENT CODE			
RECORD CODE		TYPE	
1	0	0	0
TEST DATE		LAB	
080382		BR	
RESULT BASIS		AD	

THIESS BROS. PTY. LIMITED — MINING DIVISION

PROJECT NAME	TENEMENT No.	AREA
TASMANIA	EL20/80	ROSEVALE

LAB TEST REQUEST No.
LAB TESTER/CHECKER
AUTHORISING INITIALS
SHEET

4819
C
1 of 10

COAL ANALYSIS TEST SHEET No. 1

TP 816

LABORATORY SAMPLE NUMBER	FIELD SAMPLE NUMBER	BOREHOLE NUMBER	SEAM NAME	TYPE	BASE DEPTH	THICKNESS	SIZE CODE	FRACTION		RD	SIZE/FLOAT YIELD %	PROXIMATE ANALYSIS % BY WEIGHT				C S N	SPECIFIC ENERGY	TOTAL SULPHUR % WT	COMPOSITE SAMPLES
								RAW WT.				INHERENT MOISTURE	VOLATILE MATTER	ASH	FIXED CARBON				
A60415	C 2855	C0021			49.78	0.89		RAW		182		16.2	20.5	55.2	8.1		5.80	0.19	-
16	56				50.29	0.51				143		28.5	29.3	22.5	19.7		1308	0.31	-
17	58				51.58	1.01				150		29.8	21.6	35.8	12.8		7.20	0.19	-
18	59				52.83	0.89				160		21.6	22.6	39.4	13.4		868	0.19	-
19	61				53.69	0.81				163		22.8	23.2	42.0	12.0		846	0.18	-
20	63				54.55	0.58				174		10.1	28.1	45.6	16.2		1072	0.21	-
21	64				56.24	1.69				168		23.4	19.2	47.7	9.7		592	0.16	-
22	65				58.06	1.39				164		22.9	22.3	41.2	13.6		824	0.18	-
23	66				59.57	1.51				183		17.8	18.5	56.8	6.9		456	0.15	-
24	67	C0033			27.79	0.75				202				59.1					-
25	68				29.20	0.94				237				80.5					-
26	69				31.15	0.95				225		5.0	16.0	73.2	5.8		3.18	0.07	-
27	70				31.62	0.47				162		19.4	25.8	37.5	17.3		1044	0.09	-
28	72				32.09	0.28								MISS'ING					-
29	73				32.92	0.83				183		8.0	28.4	46.4	17.2		1142	0.12	-
30	74				33.20	0.28				201				60.3					-
31	75				34.64	0.42				168		10.5	31.8	33.2	24.5		1462	0.11	-
32	77				35.82	1.18				176		8.3	28.2	43.2	20.3		1214	0.11	-
33	78				36.46	0.64				182				43.6					-
34	79				36.79	0.33				185		7.9	26.4	49.6	16.1		1048	0.11	-