

		AAS ASSAYS										FIRE ASSAY				
From	To	m	Cu	Pb	Zn	Ag	S%	Mn	Co		m	To	m	Ag	Au	
144.0	147.0	3.0	20	-	60	-	-	900	-		221.0	222.0	1.0	0.2	-	
	150.0	3.0	10	10	60	-	-	740	-			223.0	1.0	0.1	-	
	153.0	3.0	10	10	70	-	0.1	1180	-			224.0	1.0	n	n	
	156.0	3.0	270	20	60	-	-	900	-			225.0	1.0	n	n	
	159.0	3.0	160	70	90	-	-	770	-			226.0	1.0	n	n	
	162.0	3.0	150	30	110	-	-	680	-			230.0	4.0	n	n	
	165.0	3.0	50	20	80	-	-	660	-			240.0	10.0	0.1	-	
	168.0	3.0	60	10	50	-	-	790	-			250.0	10.0	-	-	
	171.4	3.4	60	20	90	-	0.1	1010	-			260.0	10.0	0.2	-	
	174.0	2.6	70	60	220	-	-	1840	10			270.0	10.0	-	-	
	177.0	3.0	80	40	180	-	-	1830	10			280.0	10.0	-	-	
	180.0	3.0	190	260	220	-	0.2	1730	10			290.0	10.0	0.3	-	
	183.0	3.9	60	90	190	-	0.3	2150	10			300.0	10.0	-	-	
	186.0	3.0	50	100	210	-	0.2	2150	10			310.0	10.0	-	-	
	189.0	3.0	50	50	160	-	0.1	1760	10			320.0	10.0	-	-	
	192.0	3.0	80	30	140	-	0.1	1950	10			330.0	10.0	-	-	
	195.0	3.0	200	30	150	-	0.3	1770	10			340.0	10.0	0.4	-	
	198.0	3.0	160	30	200	-	-	2400	-			355.2	15.2	0.9	-	
	201.0	3.0	60	70	200	-	0.1	1800	-							
	204.0	3.0	70	20	170	-	0.2	1800	-							
	207.0	3.0	100	20	220	-	0.2	1800	10							
	210.0	3.0	60	30	220	-	-	2250	-							
	213.0	3.0	40	50	260	-	0.2	2270	-							
	216.0	3.0	100	20	190	-	0.2	1350	-							
	218.5	2.5	100	30	240	-	-	1500	-							
	221.0	2.5	160	40	270	-	0.7	1350	30							
	222.0	1.0	70	20	130	-	0.6	1120	10							
	223.0	1.0	90	40	130	-	3.1	700	30							
	224.0	1.0	410	180	560	-	7.7	560	460							
	225.0	1.0	230	220	620	-	7.8	60	310							
	226.0	1.0	370	1150	1400	-	13.3	160	820							
	230.0	4.0	70	100	320	-	0.8	1200	40							
	235.0	5.0	50	120	370	-	1.2	1400	70							
	240.0	5.0	20	40	250	-	0.2	1400	-							
	245.0	5.0	20	100	200	-	0.4	960	60							
	250.0	5.0	20	40	150	-	-	730	-							
	255.0	5.0	10	20	170	-	0.2	860	-							
	260.0	5.0	70	180	270	-	0.2	1300	-							
	265.0	5.0	20	200	220	-	0.2	1550	-							
	270.0	5.0	20	60	160	-	0.2	800	-							
	275.0	5.0	30	340	250	-	0.9	1200	90							
	280.0	5.0	40	120	210	-	0.3	1100	20							
	285.0	5.0	30	140	180	-	1.0	970	100							
	290.0	5.0	30	380	360	-	0.4	1300	20							
	295.0	5.0	20	220	200	-	0.1	1000	-							
	300.0	5.0	10	40	70	-	0.1	450	-							
	305.0	5.0	10	220	90	-	0.1	560	-							

A07754 Detection Limits: 10 ppm Cu, Pb, Zn, Mn, Co  
 2 ppm Ag (AAS)  
 0.1% S  
 0.1 ppm Ag, Au (Fire Assay)

- = Less than Detection Limit  
 n = Not Assayed

749207