

Sample No.	-80# Total Extraction						-80# Cold Extraction					
	Cu	Pb	Zn	Mn	Fe%	Co	Cu	Pb	Zn	Mn	Fe%	Co
27569 ²²⁶⁰⁶ ✓	-	-	-	-	0.1	-	-	-	-	-	-	-
27570 ⁷ ✓	-	20	30	70	0.9	-	-	-	-	40	0.2	-
27571 ⁸ ✓	-	30	30	380	1.0	-	-	10	10	320	0.3	-
27572 ⁹ ✓	-	20	50	530	1.0	10	-	-	30	360	0.4	-
27573 ⁶¹⁰ ✓	-	20	30	160	1.0	-	-	-	10	100	0.2	-
27574 ¹¹ ✓	-	10	20	260	0.7	-	-	-	-	180	0.4	-
27575 ¹² ✓		NOT ASSAYED						NOT ASSAYED				
27576 ¹³ ✓	-	20	20	50	0.6	-	-	-	-	-	0.2	-
27577 ¹⁴ ✓	-	30	40	250	0.1	-	-	-	20	220	0.3	-
27578 ¹⁵ ✓	-	20	30	140	0.7	-	-	-	-	110	0.2	-
27579 ¹⁶ ✓	-	40	40	380	1.9	-	-	-	10	250	0.5	-
100 27580 ¹⁷ ✓	10	30	30	160	1.3	-	-	-	-	100	0.2	-
27581 ⁶¹⁸ ✓	20	30	40	100	1.4	-	20	-	10	60	0.2	-
27582 ²²⁶²⁶ ✓	20	50	30	170	0.6	-	-	30	10	170	0.3	-
27583 ²²⁶⁰² ✓	10	10	20	210	0.9	-	-	-	-	40	-	-
" 27584 ²²⁷²³ ✓	1050	70	80	270	4.1	20	800	40	20	90	0.3	-
" 27585 ²²⁷⁸⁵ ✓	750	130	70	640	1.2	-	720	100	60	470	0.6	-
" 27586 ²²⁷⁸⁸ ✓	80	100	80	260	3.9	-	40	30	10	150	0.3	-
27587 ⁵⁷ ✓	70	60	70	260	1.7	-	40	30	40	140	0.2	-
27588 ⁶⁰ ✓	40	60	50	800	2.7	20	20	20	20	370	0.3	-
" 27589 ⁶¹ ✓	100	70	70	1100	4.7	20	40	30	10	500	0.4	-
27590 ⁶² ✓	40	90	80	1450	3.3	20	30	40	30	800	0.5	-
27591 ⁶³ ✓	30	80	50	1050	3.2	20	20	40	10	500	0.4	-
27592 ⁶⁴ ✓	-	-	10	60	0.4	-	-	-	-	20	0.1	-
27593 ⁶⁵ ✓	20	70	40	80	3.3	-	-	20	-	240	0.3	-
27594 ⁶⁶ ✓	10	30	30	700	1.1	-	-	10	10	50	0.2	-
27595 ⁶⁷ ✓	-	20	10	140	0.5	-	-	-	-	80	0.2	-
27596 ⁶⁸ ✓	10	80	20	120	1.8	-	-	50	10	580	1.2	-
27597 ⁶⁹ ✓	20	40	30	1050	1.0	-	10	30	20	280	0.5	-
27598 ⁷⁰ ✓	40	30	20	440	0.6	-	30	10	10	30	0.2	-
27599 ⁷¹ ✓	120	80	40	50	1.2	-	80	50	10	80	0.4	-
" 27600 ²²⁷⁴⁹ ✓	80	70	70	230	2.6	-	50	40	20	120	0.3	-
27601 ²²⁷⁰⁰ ✓	60	60	60	770	1.6	-	20	20	20	390	0.2	-
27602 ⁷⁰¹ ✓	40	40	40	390	0.7	-	30	20	20	270	0.2	-

Detection
Limit

10 10 10 10 0.1 10 10 10 10 10 0.1 10
Values expressed in ppm unless otherwise stated