

APPENDIX M Continued

Sample No.	-80# Total Extraction						-80# Cold Extraction					
	Cu	Pb	Zn	Mn	Co	Fe%	Cu	Pb	Zn	Mn	Co	Fe%
21236 41 ✓	60	50	20	300	-	1.4	50	50	-	180	-	0.5
21237 40 ✓	50	40	20	120	-	0.9	30	20	-	60	-	0.2
21238 39 ✓	100	90	100	410	20	3.2	50	50	20	170	-	0.4
21239 37 ✓	80	100	50	360	-	2.1	50	60	10	150	-	0.5
21240 38 ✓	50	80	40	760	10	1.9	40	40	20	340	-	0.5
21241 42 ✓	30	20	20	60	-	0.6	20	10	-	30	-	0.3
21242 43 ✓	90	80	80	740	20	3.6	40	40	40	410	-	1.5
21243 49 ✓	130	80	140	940	40	5.8	50	40	50	430	-	1.0
21244 50 ✓	70	80	80	550	30	3.9	30	40	30	360	-	0.7
21245 51 ✓	100	110	70	670	20	2.9	60	80	20	330	-	0.6
21246 54 ✓	90	160	110	2200	50	3.3	50	120	60	1100	-	1.0
21247 57 ✓	120	110	120	870	20	5.8	50	60	30	450	-	0.7
21248 55 ✓	100	100	90	970	40	4.2	40	50	20	530	-	0.5
21249 69 ✓	30	50	10	-	-	0.3	20	40	-	-	-	0.1
21250 65 ✓	130	540	80	3900	70	4.0	120	510	60	2100	-	1.4
21251 64 ✓	30	70	10	30	-	0.3	30	30	-	10	-	0.2
21252 63 ✓	90	70	40	60	-	1.7	70	50	-	20	-	0.5
21253 62 ✓	60	100	20	160	-	0.9	50	70	10	120	-	0.5
21254 60 ✓	310	180	310	2800	100	6.6	210	120	110	1400	-	1.6
21255 61 ✓	250	140	140	4800	110	7.9	140	70	40	1800	-	0.9
21256 66 ✓	30	30	20	40	-	0.9	20	20	-	20	-	0.3
21257 67 ✓	100	90	100	1500	30	3.9	90	70	40	600	-	0.4
21258 68 ✓	100	70	80	1200	30	5.1	80	60	30	590	-	0.6
21259 59 ✓	110	80	180	4300	110	5.8	80	60	70	2000	-	0.7
21260 56 ✓	130	40	70	630	10	3.2	80	90	10	340	-	0.8
21261 58 ✓	190	100	110	2700	100	6.4	80	40	20	1100	-	0.5
21262 53 ✓	110	70	140	1700	50	3.7	60	30	40	730	-	0.8
21263 52 ✓	70	70	70	260	30	3.0	40	40	20	130	-	0.5
21264 23044 ✓	60	60	40	350	30	2.7	40	40	10	170	-	0.7
21265 5 ✓	60	50	30	80	-	1.1	50	30	10	50	-	0.3
21266 6 ✓	130	100	140	1400	40	3.9	70	70	60	680	-	0.7
21267 7 ✓	50	40	60	620	10	1.8	50	30	30	370	-	0.7
21268 8 ✓	150	80	110	2000	30	2.0	120	40	70	1100	20	0.6
21269 23070 ✓	50	50	70	580	20	2.6	30	10	30	210	-	0.4
Detection Limit	10	10	10	10	10	0.1	10	10	10	10	10	0.1