

ROCK CHIP ASSAYS

Sample Number	Type of Sample	AAS					Fire	
		Cu	Pb	Zn	Ag	S	Ag	Au
27320	Random	.14	.03	.03	7	4.1		
27321	Pyrite	.06	.04	.01	10	15.1		
27322	N wall	.08	.03	.02	9	6.4		
27323	S wall	.05	.02	.02	6	3.9		
27324	Random	.48	.01	.04	7	0.9		
27326	Random	-	.08	.05	-	-		
27327	Random	.05	.31	.04	-	0.2		
27328	Random	.06	.06	.08	-	0.2		
27329	Random	.09	.25	.13	13	0.3		
27330	Random	.02	.08	.07	2	0.2		
27335	Random	.18	-	.02	-	0.6		
27336	Random	.12	.02	.02	-	0.3		
27337	Random	-	.05	.04	-	-		
27338	Picked	.20	4.0	5.7	160	5.4		
27339	Pyrite	.02	.09	.06	4	4.3		
27340	Picked	.03	.95	2.3	4	1.5		
27342	Picked	.93	.03	.05	7	1.6		
27405	Random	.61	.07	.21	14	1.0	11	0.2

Cu,Pb,Zn in % cut-off limit 0.01%
 S in % cut-off limit 0.1%
 AAS Ag in ppm, cut-off limit 2 ppm
 Fire Ag,Au in ppm, cut-off limit 0.1ppm
 - = below cut-off limit
 na = not assayed



- ☐ POWER LINE & PYLONS
- BUILDING
- ✕ FLYING FOX
- PIT
- COSTEAN TRENCH
- ≡ ADIT
- ⊠ SHAFT (Depth metre)
- OPEN CUT
- ⊞ ALLUVIAL WORKINGS
- ⊞ DUMP
- SEALED ROAD BRIDGE
- VEHICULAR TRACK
- LOGGING TRACK BULLDOZER SCAR
- WALKING TRACK
- RAILWAY TRAMWAY ABANDONED
- △ PROMINENT PEAK
- △ TRIG STATION
- BENCH MARK
- SPOT ELEVATIONS
- RIVER CREEK
- LAKE
- SWAMP

749340


THE MOUNT LYELL MINING & RAILWAY COMPANY LTD.

E.L. 9/66
 DORA - SPICER AREA
 ROCK CHIP ASSAYS
 1980-82

SCALE 1:5000
 DATE 16-6-82

DRAWN BY M.H.
 CHECKED BY H.D. S.J.E.

FIG. 34
 A1-177-9



82-1791 (2/3)