



Assays p.p.m.

From	To	Cu	Pb	Zn	Ag	S%	Mn	Ba
0	10m							
	20m							
	30m							
	40m							
	50m	60	70	150	-	-	1900	200
	60m	150	20	220	-	0.1	2900	300
	70m	70	200	550	-	-	3500	200
	80m	180	220	550	2	0.2	2100	700
	90m	160	850	800	6	1.3	1700	300
	100m	150	2500	530	2	0.2	1000	300
	110m	50	60	580	-	-	1100	100
	120m	20	50	600	-	-	1100	-
	130m	130	30	140	-	-	290	100
	140m	30	-	150	-	0.1	520	-
	150m	20	20	320	-	-	980	-
	160m							
	170m							
	180m	80	30	620	-	0.1	1000	-
No.	28721	40	20	580	-	N.A.	780	
	28722	40	10	260	-	N.A.	820	
	28723	50	4000	860	-	N.A.	1050	
	28380	120	1300	680	22	N.A.	1300	
	28381	30	90	870	3	N.A.	1600	
Defection	Limit	10	10	10	2	0.1	10	100

No outcrop

No outcrop

All samples assayed by AAS at Mt.Lyell.

749366

5 cm

THE MOUNT LYELL MINING & RAILWAY COMPANY LIMITED

East Tyndall
Rock Chip Geochemistry
L15N. Logging Track

FIG. 47

SCALE 1:5000 DRAWN R.K. DATE JUNE 1982 DRAFTSMAN T.G.D.S. A4-229

82-1791 (3/3)