

## FED 20 SUMMARY - ASSAY DATA

FROM	TO	LENGTH (m)	AVERAGE WEIGHTED ASSAYS						
			Sn	Acid Sol. Sn.	Cu	S	Pb	Zn	Ag g/t
30	38	8	0.72	0.47	0.68	15.95	0.12	3.09	122.8
30	47	17	0.39	0.26	0.14	9.56	0.06	1.50	66.6
30	67	37	0.26	0.12	0.21	7.02	0.03	0.86	33.3

FED 21; length 117.0m  
dip 53°  
bearing 318 AMG

FED 21 was intended to test the "heel" of the "inverted gumboot". The hole was drilled from south of the target and designed to intersect at 30m depth. (below surface). The hole intersected mineralisation between 31.4m and 70.3m. Mineralisation consisted of abundant (up to 20%) disseminated pyrite. The average grain size of the pyrite is between 1-8mm.

## FED 21 SUMMARY - ASSAY DATA

FROM	TO	LENGTH (m)	AVERAGE WEIGHTED ASSAYS						
			Sn	Acid Sol. Sn.	Cu	S	Pb	Zn	Ag g/t
34	50	16	0.54	0.01	0.01	5.7	0.01	0.02	1
62	65	3	0.33	0.01	0.01	10.9	0.01	0.01	1