

Table 2 cont.

LANGLOH COAL SERIES CALCULATED SEAM ASSAY RESULTS (RAW COAL, AIR DRIED)

COMPOSITES CALCULATED FROM WEIGHTED AVERAGES OF PLIES

(WHERE A-B INTERBURDEN (Sh 1) ≤ 15cm SEAMS A, B+Sh1 ARE COMBINED)

HOLE	SEAM	THICKNESS (M) (DENSITY LOG)	RELATIVE DENSITY	% MOISTURE	% ASH	% VOLATILES	% FIXED CARBON	SPECIFIC ENERGY MJ/Kg	% SULPHUR
H-22	A	1.60	1.54	5.5	26.4	21.9	46.7	20.94	0.21
	B	1.47	1.48	4.9	17.2	26.2	51.7	24.44	0.33
	C	1.35	1.51	4.6	18.5	27.8	49.1	24.24	0.33
	TOTAL MEAN	4.42	1.51	5.0	21.0	25.1	48.9	23.11	0.29
H-23	A+Sh1+B	2.35	1.60	3.5	31.5	16.2	48.8	20.14	0.28
	C	1.21	1.52	2.8	18.3	19.2	59.7	26.38	0.38
	TOTAL MEAN	3.56	1.57	3.3	27.1	17.2	52.4	22.20	0.31
H-24	A	1.07	1.93	3.0	41.1	9.8	46.1	19.38	0.33
	B	0.92	1.68	2.6	25.4	9.3	62.7		
	C**								
H-28	A+Sh1+B	2.08	1.56	3.1	25.5	19.0	52.4	23.58	0.36
	C	1.36	1.50	2.7	19.2	20.6	57.5	26.42	0.36
	TOTAL MEAN	3.44	1.53	2.9	23.1	19.6	54.4	24.68	0.36

** Seam C broken - incomplete