



SGS Australia Pty. Ltd.

REPORT No: SL 2346

Page 2 of 6

Analysis	Sample Ref.					
	H-20 1	H-20 2	H-20 3	H-20 4	H-20 5	H-20 6
Total Moisture %						
Moisture %	5.7	4.2	3.8	3.0	3.6	3.6
Ash %	36.3	26.6	24.3	17.6	22.5	24.1
Volatile Matter %	17.4	20.0	19.9	24.3	22.5	21.6
Fixed Carbon %	40.6	49.2	52.0	55.1	51.4	50.7
Crucible Swelling No.						
Total Sulphur %						
Specific Energy Mj/kg						
Relative density	1.62	1.53	1.52	1.44	1.49	1.50
Mass as received(g)	2047.2	1614.8	1283.0	1184.2	1222.0	1316.0

Analysis	Sample Ref.					
	H-22 7	H-22 8	H-22 9	H-22 10	H-22 11	H-22 12
Total Moisture %						
Moisture %	5.7	5.4	5.0	4.9	4.7	4.6
Ash %	28.8	24.0	20.0	14.4	13.4	21.9
Volatile Matter %	21.0	22.8	23.9	28.5	29.3	26.8
Fixed Carbon %	44.5	47.8	51.1	52.2	52.6	46.7
Crucible Swelling No.						
Total Sulphur %						
Specific Energy Mj/kg						
Relative density	1.56	1.53	1.53	1.44	1.41	1.59
Mass as received(g)	1679.3	1677.5	1541.1	1449.2	907.3	1301.6

BASIS RESULTS REPORTED ON

AIR DRIED

COLIN MEADS
MANAGER - LABORATORIES



This Laboratory is registered by the National Association of Testing Authorities, Australia. The test(s) reported herein have been performed in accordance with its terms of registration. This document shall not be reproduced except in full.