

Sample No.	-80# Total Extraction						-80# Gold Extraction					
	Cu	Pb	Zn	Mn	Co	Fe%	Cu	Pb	Zn	Mn	Co	Fe%
21372	40	40	70	150	20	2.3	20	-	30	80	-	0.2
21373	60	80	140	3200	50	2.2	50	60	90	1700	10	0.7
21374	30	30	10	40	-	0.3	20	10	-	20	-	0.2
21375	30	30	50	430	20	1.6	20	10	20	320	-	0.5
21376	100	160	90	5000	110	4.1	50	120	30	2300	30	0.9
21377	210	40	120	380	40	7.6	70	10	60	220	10	1.4
21378	80	60	90	230	30	2.9	30	40	10	120	-	0.8
21379	120	60	190	1500	70	5.5	30	20	50	1100	20	1.1
21380	200	70	200	2500	100	6.0	70	40	50	1500	30	0.8
21381	190	100	150	2400	90	10.0	70	20	60	1800	40	3.0
21382	130	180	240	3400	100	6.4	40	140	110	2100	40	1.9
21383	140	40	140	1500	60	8.0	40	10	30	1100	20	1.7
21384	70	30	70	120	20	2.6	30	10	20	50	-	0.8
21385	90	60	160	1000	30	5.4	40	30	70	750	-	1.0
21386	10	30	30	60	-	0.6	10	-	10	30	-	0.1
21387	10	50	50	120	-	0.6	10	20	30	90	-	0.2
21388	70	90	240	2800	-	1.8	50	40	150	1400	-	0.2
21389	50	120	100	770	20	1.8	20	70	40	420	-	0.4
21390	90	70	190	1800	60	5.4	30	20	70	950	10	0.7
21391	10	40	40	200	-	0.5	10	-	30	150	-	0.2
21392	10	50	40	400	-	0.8	-	10	30	270	-	0.4
21393	-	10	-	-	-	-	-	-	-	-	-	-
21394	-	20	20	20	-	0.2	-	10	10	10	-	-
21395	-	20	20	40	-	0.4	-	-	10	30	-	-
21396	-	10	-	-	-	0.1	-	-	-	-	-	-
21397	80	60	60	250	10	5.0	30	-	10	80	-	0.4
21398	60	60	70	480	20	3.8	30	10	10	320	-	0.4
21399	-	30	20	60	-	0.5	-	-	-	40	-	-
21400	40	70	160	1100	20	2.5	30	20	70	600	-	0.3
21401	40	50	20	70	-	1.9	30	-	-	20	-	0.4
21402	60	80	50	100	-	3.2	40	10	-	10	-	0.2
21403	-	30	30	260	-	0.5	-	-	10	180	-	0.2
21404	-	20	-	-	-	0.2	-	-	-	-	-	-
21405	-	30	10	50	-	0.2	-	-	-	30	-	-
Detection Limit	10	10	10	10	10	0.1	10	10	10	10	10	0.1