

APPENDIX M Continued

524041

Sample No.	-80# Total Extraction						-80# Cold Extraction					
	Cu	Pb	Zn	Mn	Co	Fe%	Cu	Pb	Zn	Mn	Co	Fe%
21406	-	40	20	40	-	0.5	-	-	10	30	-	0.1
21407	-	20	-	-	-	-	-	-	-	-	-	-
21408	10	30	40	80	-	0.6	-	10	20	50	-	0.3
21409	-	20	-	20	-	0.1	-	-	-	10	-	-
21410	-	20	-	-	-	-	-	-	-	-	-	-
21411	220	120	240	2700	60	6.1	170	80	120	1800	30	0.6
21412	130	80	120	1700	30	1.5	100	30	80	940	10	0.1
21413	290	130	80	2700	60	2.4	210	80	30	1700	30	0.4
21414	130	90	140	5000	70	6.0	90	30	60	2200	30	0.8
21415	120	90	30	80	-	2.9	80	40	-	50	-	0.5
21416	50	60	90	260	-	3.7	20	10	30	120	-	0.2
21417	40	60	100	600	10	4.6	20	10	30	310	-	0.7
21418	60	60	120	1800	30	4.1	40	10	50	970	10	0.6
21419	80	70	140	750	30	2.4	50	20	90	630	20	0.5
21420	80	80	40	280	20	2.6	50	-	20	190	-	0.4
21421	20	40	40	210	-	1.2	10	-	20	130	-	0.2
21422	10	30	40	200	-	0.1	-	-	20	110	-	-
21423	10	40	10	50	-	1.2	-	-	10	-	-	-
21424	40	50	50	830	40	2.5	30	-	20	750	-	0.3
21425	10	20	10	30	-	0.7	-	-	-	-	-	0.1
21426	-	20	30	220	-	1.0	-	-	-	120	-	0.1
21427	10	30	30	300	-	1.8	-	-	10	160	-	0.3
21428	20	20	-	-	-	0.3	10	-	-	-	-	-
21429	-	20	10	50	-	0.6	-	-	-	20	-	0.1
21430	20	30	20	10	-	0.6	-	-	10	-	-	0.3
21431	-	20	-	-	-	0.1	-	-	-	-	-	-
21432	-	20	-	-	-	0.2	-	-	-	-	-	-
21433	-	40	30	170	-	1.3	-	-	10	100	-	0.3
21434	40	50	30	50	-	2.7	20	-	-	20	-	0.5
21435	10	30	10	100	-	0.5	-	-	-	80	-	0.1
21436		NOT	ASSAYED					NOT	ASSAYED			
21437		NOT	ASSAYED					NOT	ASSAYED			
21438		NOT	ASSAYED					NOT	ASSAYED			
21439		NOT	ASSAYED					NOT	ASSAYED			
Detection Limit	10	10	10	10	10	0.1	10	10	10	10	10	0.1