

CSR Limited

COAL ANALYSIS TEST NO. 1 BY HOLE

ATF E12080  
Launceston

TENEMENT 2080

Seam	LSN	FSN	Ty RB	Base Thick	Size Fraction	RD	Yield	PROXIMATES	% by WEIGHT	Fuel C	S.E.	Total	Test Lab
WS			pe	Depth	-+ (Raw Wt)			IM VM ASH FC		Ratio S	MJ/ks	Sulphur	Date
Drillhole C0082													
*****													
A68773	C00336		1 AD	69.91	0.36	R	/03.27 1.92	8.5 23.4	54.5 13.6	0.58	8.26	0.26	01/84 BR
A68774	C00337		1 AD	70.57	0.66	R	/06.78 2.21	5.6 16.0	74.9 3.5	0.22	2.20	0.13	01/84 BR
A68775	C00338		1 AD	71.24	0.67	R	/04.39 1.60	13.1 32.3	31.4 23.2	0.72	14.04	0.25	01/84 BR
A68776	C00339		1 AD	71.47	0.23	R	/02.01 1.93	7.6 23.8	57.4 11.2	0.47	7.56	0.19	01/84 BR
A68777	C00340		1 AD	72.47	1.00	R	/08.88 1.70	18.2 24.2	43.3 14.3	0.59	9.16	0.19	01/84 BR
A68778	C00341		1 AD	72.71	0.24	R	/02.21 2.21	6.1 19.9	69.1 4.9	0.25	3.72	0.11	01/84 BR
A68779	C00342		1 AD	73.92	1.21	R	/09.08 1.60	16.4 29.7	33.9 20.0	0.67	12.74	0.22	01/84 BR
A68780	C00343		1 AD	75.04	1.12	R	/08.59 1.57	18.7 29.4	29.9 22.0	0.75	13.12	0.19	01/84 BR
A68781	C00344		1 AD	75.88	0.84	R	/06.17 1.57	18.5 28.9	28.4 24.2	0.84	13.22	0.20	01/84 BR
A68782	C00345		1 AD	76.80	0.92	R	/06.91 1.56	21.5 27.4	27.6 23.5	0.86	12.58	0.19	01/84 BR
A68783	C00346		1 AD	76.98	0.18	R	/01.28 1.81	10.9 28.4	44.1 16.6	0.58	9.96	0.18	01/84 BR
A68784	C00347		1 AD	77.37	0.39	R	/04.01 2.43	4.3 21.4	74.3 0.0	0.00	2.26	0.06	01/84 BR

\*\*\* END OF REPORT TC52-09 \*\*\*

003

397112