

ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD.
MINERAL RESOURCES DIVISION - TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. CHP 263
SHEET No. 1

LABORATORY						ANALABS, Coeee													GRID CO-ORDS: A.M.G. CO-ORDS: 5,370,399mN 394,973.5mE COLLAR R.L.: 515m COLLAR DIP: -45° AZIMUTH: 090° A.M.G. TOTAL DEPTH: 203.8m	
						ANALYTICAL TECHNIQUE														
						402	401	309	108	402	108	114	108	108	108	108	108	108		
DETECTION LIMIT						XRF	XRF	Fire Assay	AAS	XRF	AAS	AAS	AAS	AAS	AAS	AAS	AAS	AAS		
						3	10	0.008	0.5	3	10	1	5	5	5	50	5	5		
Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)													COMMENTS	
						Sn	W	Au	Ag	Sb	Bi	As	Cu	Pb	Zn	Fe%	Mn	Cr		
63001	Chip	4.0	7.4	2.7	3.4	21	X	X	X	6	X	58	60	70	150	6.50	180	120		
002	"	7.4	10.5	3.1	3.1	49	X	X	X	6	X	60	70	75	135	5.75	260	75		
003	"	10.5	13.9	3.4	3.4	X	11	X	X	X	X	19	30	15	165	6.75	410	95		
004	"	13.9	16.0	2.1	2.1	X	X	X	X	X	X	10	120	15	215	7.45	1050	80		
005	"	16.0	17.7	1.7	1.7	X	X	X	X	7	X	52	110	75	120	5.00	1200	35		
006	"	17.7	21.2	0.5	3.5	X	X	X	X	4	X	56	140	105	85	4.35	60	30		
007	"	21.2	24.2	0.3	3.0	2	X	X	0.5	X	X	65	75	265	155	4.20	2450	50		
008	"	24.2	27.2	1.0	3.0	2	X	X	X	4	X	27	45	100	125	2.35	195	40		
009	"	27.2	29.0	1.3	1.8	X	X	X	X	4	X	22	45	115	180	3.05	85	25		
63010	"	29.0	31.0	1.5	2.0	X	X	X	0.5	2	X	39	40	100	85	2.80	80	20		
010	"	31.0	34.0	0.5	3.0	X	X	X	0.5	8	X	60	80	310	165	4.60	275	55		
012	"	34.0	37.9	1.65	3.9	X	X	X	0.5	39	X	80	60	130	150	4.25	520	55		
013	"	37.9	39.8	0.9	1.9	16	X	X	0.5	10	X	28	130	25	195	6.00	515	70		
014	"	39.8	42.3	2.5	2.5	143	19	X	X	12	X	77	125	5	150	8.65	930	55	Fault zone	
015	"	42.3	45.2	2.9	2.9	153	28	X	0.5	10	X	230	80	20	175	11.50	3450	85	Siliceous breccia.	
016	"	45.2	47.9	2.7	2.7	218	X	X	1.0	25	X	130	230	40	80	4.05	280	100		
017	"	47.9	49.9	2.0	2.0	13	X	X	0.5	6	X	110	85	10	165	7.25	1700	95		
018	"	49.9	51.8	1.9	1.9	X	17	X	X	4	X	76	100	60	225	5.30	3250	115		
019	"	51.8	53.5	1.1	1.7	X	X	X	X	X	X	31	170	5	265	5.15	480	70		
63020	"	53.5	55.0	1.4	1.5	67	10	X	0.5	26	X	90	325	110	350	9.45	3050	65		
021	"	55.0	58.0	2.0	3.0	21	X	X	0.5	21	X	82	210	305	800	11.00	8100	50		
022	"	58.0	61.0	1.4	3.0	X	16	X	X	44	X	65	105	195	515	9.25	3.20%	35		
023	"	61.0	64.5	3.5	3.5	X	12	X	0.5	3	X	30	45	80	245	2.45	2200	35		
024	"	64.5	67.6	3.1	3.1	X	X	X	1.0	7	X	16	80	65	95	3.45	1350	40		
025	"	67.6	69.8	2.2	2.2	X	X	X	1.0	7	X	35	90	80	120	2.15	915	45		
026	"	69.8	72.6	2.8	2.8	X	X	X	X	X	X	15	65	15	75	5.70	1350	175		
027	"	72.6	74.9	2.3	2.3	X	X	X	0.5	X	X	28	50	40	150	5.40	2550	25		
028	"	74.9	77.5	2.6	2.6	X	15	X	X	X	X	13	65	40	120	3.20	1550	25		
029	"	77.5	81.4	3.9	3.9	X	X	X	X	X	X	8	50	25	60	4.25	1250	30		
63030	"	81.4	83.15	1.75	1.75	X	X	X	X	X	X	19	60	75	250	3.50	1800	15		
031	"	83.15	84.7	1.55	1.55	X	X	X	X	3	X	14	145	15	80	4.50	905	130		
032	"	84.7	86.4	1.7	1.7	X	10	X	0.5	2	X	19	90	75	150	4.65	1700	80		
033	"	86.4	87.9	1.5	1.5	X	11	X	X	X	X	9	75	10	105	4.95	945	125		
034	"	87.9	90.9	3.0	3.0	X	X	X	X	X	X	13	90	40	140	6.05	780	70		
035	"	90.9	92.7	1.8	1.8	X	13	X	0.5	X	X	8	140	70	195	6.75	1350	70		
036	"	92.7	96.0	3.3	3.3	X	X	X	0.5	X	X	13	80	75	145	5.20	2100	115		
037	"	96.0	99.0	3.0	3.0	X	X	X	0.5	X	X	3	95	15	140	6.40	1300	65		
038	"	99.0	102.0	3.0	3.0	X	10	X	X	X	X	2	35	10	80	4.30	1400	80		
039	"	102.0	105.1	3.1	3.1	X	13	X	0.5	X	X	1	65	5	75	5.65	1250	60		
63040	"	105.1	107.5	2.4	2.4	X	X	X	0.5	X	X	6	80	45	310	4.30	1150	70		
041	"	107.5	110.0	2.5	2.5	X	X	X	0.5	X	X	10	60	65	405	5.35	1200	115		
042	"	110.0	112.1	2.1	2.1	X	16	X	0.5	X	X	10	55	45	620	5.70	1300	90		
043	"	112.1	115.0	2.9	2.9	X	X	X	X	2	X	6	120	30	170	6.05	1300	140		
044	"	115.0	118.0	3.0	3.0	X	10	X	0.5	X	X	5	110	40	260	7.35	1050	145		