

452

ELECTROLYTIC ZINC COMPANY OF ASIA LTD.
MINERAL RESOURCES DIVISION - TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. DDH CHP 263
SHEET No. 2

Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)													COMMENTS
						Sn	W	Au	Ag	Sb	Bi	As	Cu	Pb	Zn	Fe%	Mn	Cr	
63045	Chip	118.0	120.6	2.6	2.6	X	X	X	0.5	X	X	5	135	90	145	7.25	1550	145	
046	"	120.6	123.0	2.4	2.4	X	X	X	0.5	X	X	6	95	60	215	6.15	1350	110	
047	"	123.0	126.0	3.0	3.0	X	X	X	0.5	X	X	10	110	40	185	6.50	1600	110	
048	"	126.0	129.0	3.0	3.0	X	10	X	0.5	5	X	6	100	25	160	6.20	1100	125	
049	"	129.0	131.9	2.9	2.9	X	X	X	0.5	2	X	12	45	30	80	5.75	1950	100	
63050	"	131.9	135.0	3.1	3.1	X	X	X	0.5	3	X	6	120	10	85	6.15	1500	35	
051	"	135.0	138.0	3.0	3.0	X	X	X	X	5	X	13	75	5	105	6.85	1500	65	
052	"	138.0	141.0	3.0	3.0	X	X	X	0.5	X	X	21	100	X	95	6.15	1450	60	
053	"	141.0	144.0	3.0	3.0	X	X	X	X	X	X	4	90	X	100	7.50	1250	45	
054	"	144.0	147.6	3.6	3.6	X	X	X	0.5	X	X	14	95	X	105	7.65	1800	45	
055	"	147.6	149.0	1.4	1.4	X	X	X	0.5	2	X	14	180	15	60	4.45	1650	25	
056	"	149.0	151.0	2.0	2.0	X	X	X	0.5	7	X	23	60	45	45	3.10	1050	135	
057	"	151.0	153.3	2.3	2.3	X	X	X	0.5	5	X	27	150	15	50	4.05	790	105	
058	"	153.3	155.7	2.4	2.4	X	X	X	0.5	X	X	10	30	X	40	2.35	435	25	
059	"	155.7	157.2	1.5	1.5	X	X	X	0.5	X	X	25	55	50	70	2.75	235	205	
60360	"	157.2	160.8	3.6	3.6	X	X	X	0.5	4	X	12	20	5	45	2.55	625	15	
061	"	160.8	162.2	1.4	1.4	X	18	X	0.5	2	X	15	20	10	50	230	305	65	
062	"	162.2	165.2	3.0	3.0	X	X	X	0.5	3	X	12	20	5	120	2.45	555	20	
063	"	165.2	168.3	3.1	3.1	X	X	X	0.5	X	X	15	30	20	50	3.90	790	100	
064	"	168.3	171.0	2.7	2.7	X	10	X	0.5	5	X	20	25	30	60	2.85	425	15	
065	"	171.0	174.0	3.0	3.0	X	X	X	0.5	5	X	19	20	15	50	3.40	450	15	
066	"	174.0	177.0	3.0	3.0	X	X	X	0.5	10	X	25	20	15	35	3.20	560	20	
067	"	177.0	180.0	3.0	3.0	X	11	X	0.5	X	X	14	25	X	40	3.00	475	50	
068	"	180.0	183.0	3.0	3.0	3	X	X	0.5	7	X	24	35	10	30	2.60	660	15	
069	"	183.0	184.7	1.7	1.7	2	12	X	1.0	28	X	53	45	50	70	3.70	740	75	
63070	Split	184.7	185.1	0.4	0.4	X	X	X	1.0	20	X	39	55	180	510	4.75	2650	70	
071	"	185.1	185.65	0.55	0.55	X	X	X	0.5	4	X	20	10	X	90	5.55	915	55	
072	"	185.65	185.85	0.2	0.2	X	X	X	0.5	X	X	5	10	X	60	2.85	240	20	
073	"	185.85	186.1	0.25	0.25	X	X	X	X	X	X	13	15	5	85	5.15	1200	145	
074	"	186.1	187.0	0.9	0.9	X	X	X	X	X	X	13	25	X	80	4.80	1950	75	
075	"	187.0	187.6	0.6	0.6	X	X	X	X	4	X	6	10	15	180	6.35	2850	30	
076	"	187.6	188.2	0.6	0.6	X	X	X	0.5	X	X	14	90	10	135	6.60	3000	50	
077	"	188.2	188.6	0.4	0.4	X	X	X	0.5	9	X	19	250	5	110	5.55	1100	55	
078	"	188.6	189.5	0.9	0.9	X	X	X	0.5	3	X	14	100	X	90	6.15	1800	55	
079	"	189.5	190.1	0.6	0.6	X	X	X	0.5	7	X	30	20	5	75	7.40	5000	50	
63080	"	190.1	190.7	0.6	0.6	X	X	X	0.5	5	X	41	35	5	80	7.45	2450	55	
081	"	190.7	191.5	0.8	0.8	X	X	X	X	6	X	14	20	10	90	6.70	2000	35	
082	"	191.5	191.9	0.4	0.4	X	X	X	0.5	X	X	11	20	15	115	6.85	2100	40	
083	"	191.9	192.5	0.6	0.6	X	X	X	X	X	X	16	35	30	90	6.10	1650	40	
084	"	192.5	192.85	0.35	0.35	X	X	X	X	X	X	2	5	5	100	5.90	1250	50	
085	"	192.85	193.7	0.85	0.85	X	X	X	0.5	7	X	7	20	15	125	7.35	2350	25	
086	"	193.7	194.6	0.9	0.9	X	X	X	X	3	X	11	225	45	140	7.85	2400	45	
087	"	194.6	195.0	0.4	0.4	X	X	X	0.5	X	X	3	15	10	100	7.50	1550	70	
088	"	195.0	195.8	0.8	0.8	X	X	X	0.5	X	X	3	60	X	125	7.10	1050	55	
089	"	195.8	196.4	0.6	0.6	X	X	X	0.5	4	X	6	450	X	95	6.85	2000	75	
63090	"	196.4	197.2	0.8	0.8	X	X	X	0.5	2	X	3	15	X	100	6.50	780	45	
091	"	197.2	198.1	0.9	0.9	X	X	X	0.5	X	X	3	25	X	90	5.35	430	20	
092	"	198.1	199.0	0.9	0.9	X	X	X	0.5	X	X	1	20	10	105	7.00	1200	70	
093	"	199.0	199.9	0.9	0.9	X	10	X	X	4	X	3	20	X	105	6.40	1000	45	
094	"	199.9	200.8	0.9	0.9	X	X	X	X	X	X	X	10	X	100	6.65	580	15	
095	"	200.8	201.2	0.4	0.4	X	X	X	0.5	X	X	X	5	X	95	7.35	580	15	

251452