

ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD.
MINERAL RESOURCES DIVISION - TASMANIA

DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD

HOLE No. CHP 264
SHEET No. 3

Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)													COMMENTS
						Sn	W	Au	Ag	Sb	Bi	As	Cu	Pb	Zn	Fe%	Mn	Cr	
63196	Chip	213.4	215.0	1.6	1.6	X	10	X	0.5	16	X	15	60	20	85	6.85	1850	85	
197	"	215.0	217.6	2.6	2.6	X	X	X	X	23	X	13	45	20	90	7.45	1200	90	
198	"	217.6	219.8	2.2	2.2	X	X	X	0.5	16	X	19	40	10	20	2.55	420	160	
199	"	219.8	222.2	2.4	2.4	2	X	X	1.0	20	X	33	200	30	25	2.75	390	270	
63200	"	222.2	224.4	2.2	2.2	4	X	X	0.5	15	X	34	110	15	20	2.95	660	280	
201	Split	224.4	225.1	0.7	0.7	15	X	X	X	19	X	29	80	15	50	2.65	685	125	
202	"	225.1	226.2	1.1	1.1	54	X	X	X	13	X	37	160	30	95	14.50	2.40%	170	Fault zone strongly carbonated, pyritic.
203	Split	226.2	227.0	0.8	0.8	90	11	X	1.0	52	X	18	150	265	255	2.95	1700	120	
204	Chip	227.0	230.0	3.0	3.0	4	7	X	0.5	6	X	15	100	105	325	2.00	2600	145	
205	Split	230.0	231.0	1.0	1.0	X	X	X	X	6	X	18	40	10	20	2.45	890	50	
206	"	231.0	232.0	1.0	1.0	X	10	X	X	5	X	14	100	X	20	2.00	795	30	
207	"	232.0	233.0	1.0	1.0	X	X	X	X	3	X	8	75	X	15	1.25	900	45	
208	"	233.0	234.0	1.0	1.0	X	X	X	X	3	X	8	75	X	15	1.25	900	45	
209	"	234.0	234.9	0.9	0.9	X	X	X	X	3	X	18	75	X	15	1.00	355	45	
63210	"	234.9	235.8	0.9	0.9	4	X	X	X	18	X	73	160	30	30	2.45	1050	30	
211	"	235.8	236.0	0.2	0.2	10	12	X	X	16	X	21	95	40	95	3.85	2550	605	
212	"	236.0	236.3	0.3	0.3	116	19	X	2.0	96	X	80	790	625	1550	4.35	4900	280	Pyritic veined brecciated wall rock.
213	"	236.3	236.45	0.15	0.15	6450	772	0.20	155.0	968	320	1700	5100	2.36%	9.00%	19.00	1.80%	690	Massive sulphide (pyrite) vein
214	"	236.45	237.1	0.65	0.65	118	X	X	1.5	46	X	70	230	175	585	3.00	2350	260	Pyritic veined brecciated wall rock.
215	"	237.1	237.7	0.6	0.6	32	X	X	X	54	X	49	40	45	35	3.05	930	120	
216	"	237.7	238.5	0.8	0.8	5	X	X	X	34	X	42	35	30	20	2.20	440	100	
217	"	238.5	239.2	0.7	0.7	X	X	X	0.5	28	X	33	30	25	25	2.35	515	70	
218	"	239.2	240.0	0.8	0.8	X	X	X	X	34	X	38	35	30	35	2.15	320	50	
219	Chip	240.0	242.8	2.8	2.8	3	X	X	0.5	17	X	39	25	20	25	2.40	340	85	
63220	"	242.8	245.0	2.2	2.2	X	X	X	X	6	X	25	30	25	25	2.60	390	120	
221	"	245.0	247.7	2.7	2.7	X	X	X	X	6	X	15	80	15	40	2.00	615	55	
222	"	247.7	251.0	3.3	3.3	X	X	X	X	X	X	10	25	X	30	2.05	440	25	
223	"	251.0	254.0	3.0	3.0	X	X	X	X	3	X	7	15	X	25	2.15	1050	20	
224	Split	254.0	254.6	0.6	0.6	X	X	X	X	X	X	8	5	5	25	2.80	1850	50	
225	Chip	254.6	256.5	1.9	1.9	X	X	X	X	3	X	4	10	X	25	1.75	470	25	
63226	"	256.5	258.1	1.6	1.6	X	14	X	X	3	X	5	15	10	20	1.15	245	30	
		End of Hole																	