

471

ELECTROLYTIC ZINC COMPANY OF A'ASIA LTD. MINERAL RESOURCES DIVISION - TASMANIA						DIAMOND DRILL CORE GEOCHEMICAL ANALYSES RECORD													HOLE No. DDH CHP 266 SHEET No. 1		
LABORATORY  ANALYTICAL TECHNIQUE  DETECTION LIMIT						ANALABS													GRID CO-ORDS: A.M.G. CO-ORDS: 5,370,773mN 375,651mE COLLAR R.L.: 319m COLLAR DIP: -45° AZIMUTH: 087° AMG TOTAL DEPTH: 196m		
						402	401	309	108	402	108	114	108	108	108	108	108	108			108
						XRF	XRF	Fire Assay	AAS	XRF	AAS	AAS	AAS	AAS	AAS	AAS	AAS	AAS			AAS
						3	10	0.008	0.5	3	10	1	5	5	5	50	5	5			
Sample No.	Sample Type	From	To	Core Rec'd	Sample Length	METAL CONTENT (ppm unless specified)													COMMENTS		
						Sn	W	Au	Ag	Sb	Bi	As	Cu	Pb	Zn	Fe%	Mn	Cr			
63227	Chip	19.0	22.5	2.8	3.5	X	X	X	X	X	X	200	150	40	115	6.85	1350	220			
228	"	22.5	25.9	3.3	3.4	X	X	X	X	18	X	76	275	25	155	8.25	1700	365			
229	"	25.9	28.0	1.6	2.1	15	X	X	1.0	7	20	460	160	25	40	3.10	730	120			
63230	"	28.0	31.0	2.3	3.0	X	X	X	X	10	X	82	50	25	40	1.80	195	110			
231	"	31.0	34.0	2.6	3.0	X	X	0.02	0.5	10	X	150	55	15	40	2.35	110	115			
232	"	34.0	37.0	2.85	3.0	4	X	X	0.5	6	X	54	60	15	45	2.45	135	115			
233	"	37.0	40.8	2.5	3.8	X	X	X	0.5	9	X	53	40	10	30	2.40	105	100			
234	"	40.8	43.4	1.9	2.6	X	X	X	0.5	7	X	16	35	10	20	1.35	60	65			
235	"	43.4	45.8	2.2	2.4	X	X	X	X	4	X	5	45	10	30	1.75	110	80			
236	"	45.8	48.0	2.1	2.2	X	X	X	1.0	13	X	19	80	15	25	1.55	110	205			
237	"	48.0	50.5	2.5	2.5	847	X	X	0.5	6	X	82	210	10	70	1.80	160	55	Broken core zone with quartz-pyrite veins		
238	"	50.5	53.5	2.8	3.0	92	X	0.01	X	6	X	82	130	10	55	2.55	430	25			
239	"	53.5	56.3	2.8	2.8	7	X	X	0.5	3	X	13	35	5	40	2.15	450	35			
63240	"	56.3	59.0	2.7	2.7	X	X	0.10	X	3	X	18	35	10	50	2.25	465	75			
241	"	59.0	61.2	1.6	2.2	X	X	X	0.5	X	X	8	40	5	45	1.70	100	70			
242	"	61.2	63.2	1.8	2.0	X	X	X	X	X	X	8	30	5	60	2.20	260	100			
243	"	63.2	66.2	3.0	3.0	X	X	X	X	3	X	10	25	5	80	3.00	825	20			
244	"	66.2	69.2	3.0	3.0	X	X	X	X	X	X	8	20	5	70	2.20	195	40			
245	"	69.2	71.1	1.8	1.9	X	X	X	X	8	X	15	20	15	45	2.95	895	35			
246	"	71.1	73.4	2.1	2.3	X	X	X	0.5	X	X	18	20	5	20	2.15	135				
247	"	73.4	74.9	1.5	1.5	X	X	0.11	0.5	4	X	22	20	5	20	1.70	360	55			
248	"	74.9	76.8	1.9	1.9	X	X	X	0.5	7	X	20	30	10	25	1.80	570	55			
249	Split	76.8	77.5	0.7	0.7	22	X	X	1.0	16	10	39	60	30	45	2.55	935	60			
63250	"	77.5	78.1	0.6	0.6	274	X	X	2.0	11	40	1000	1700	50	70	8.40	3600	90	Quartz-pyrite veins in breccia		
251	"	78.1	78.6	0.5	0.5	44	X	X	0.5	6	X	39	130	10	25	3.25	1550	80			
252	"	78.6	79.2	0.6	0.6	15	X	X	X	7	X	80	35	5	30	2.95	830	100			
253	Chip	79.2	81.9	2.7	2.7	16	X	0.02	0.5	9	X	18	25	5	15	1.90	390	20			
254	"	81.9	84.5	2.6	2.6	3	X	X	X	6	X	16	25	5	20	2.30	185	45			
255	"	84.5	85.7	1.2	1.2	9	X	0.19	X	6	X	22	30	40	220	3.75	1850	25	Pyrrhotite-pyrite-carbonate-quartz vein		
256	"	85.7	87.5	1.8	1.8	6	X	X	X	3	X	15	50	5	30	3.45	475	35			
257	"	87.5	89.2	1.7	1.7	14	X	0.04	X	5	X	19	50	10	30	2.70	960	20			
258	Split	89.2	90.2	1.0	1.0	125	X	0.08	0.5	8	X	1850	120	5	35	4.40	1750	90	Rare thin quartz veins with Pyrite & Pyrrhotite		
259	"	90.2	90.95	0.75	0.75	28	X	X	X	X	X	36	25	5	20	1.50	350	40			
63260	"	90.95	91.15	0.2	0.2	24	X	X	X	7	X	12	50	5	30	3.45	785	85			
261	Chip	91.15	92.5	1.35	1.35	18	X	X	X	X	X	10	15	10	25	2.25	595	130			
262	"	92.5	94.7	2.2	2.2	33	X	X	X	3	X	19	20	5	20	1.95	510	55			
263	Split	94.7	95.5	0.8	0.8	X	X	X	X	X	X	47	30	10	20	2.35	245	105			
264	"	95.5	95.65	0.15	0.15	X	X	X	X	X	X	11	45	5	35	5.55	2350	100			
265	"	95.65	96.4	0.75	0.75	11	X	X	X	7	X	21	15	10	25	1.75	305	105			
266	"	96.4	97.2	0.8	0.8	18	X	X	0.5	4	X	18	35	5	40	2.85	500	60			
267	Split	97.2	97.9	0.7	0.7	16	X	X	X	11	X	12	25	5	15	2.30	320	90			
268	Chip	97.9	100.0	2.1	2.1	15	X	X	0.5	X	X	17	30	5	25	2.90	670	105			
269	"	100.0	102.0	2.0	2.0	366	X	X	0.5	9	X	62	80	20	155	3.05	960	85	2% Pyrite+Pyrrhotite stringers		

251471