






Nº 3 WORKINGS




%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
1. 0.31	<0.01	0.023	2	0.030	0.017	0.055
2.	N.A.					
3.	N.A.					
4. 0.045	<0.01	0.01	1	0.025	0.033	0.04
5. 0.57	0.022	0.017	5	0.022	0.013	0.05
6.	N.A.					
7. 0.23	0.013	0.014	4	0.010	0.019	0.034
8. 0.26	0.022	0.015	48	0.014	0.18	0.026
9. 1.26	<0.01	0.010	22	0.005	0.049	0.014
10.	N.A.					
11. 3.72	0.039	0.045	15	0.02	0.11	0.14
12. 3.50	0.048	2.90	67	0.087	0.43	0.055
13.U. 5.19	0.037	0.04	17	0.026	0.54	0.28
13.L. 1.16	0.044	0.57	42	0.236	0.38	0.024
14.U. 1.01	0.03	0.017	15	0.006	0.042	0.03
14.L. 3.10	0.039	0.054	56	0.01	0.048	0.026
15. 0.70	0.013	0.003	15	0.008	0.045	0.022
16. 0.97	0.305	0.024	158	0.028	0.052	0.040
17. 0.40	<0.01	0.026	6	0.007	0.016	0.007
18. 0.87	<0.01	0.028	3	0.005	0.017	0.003
19. 0.006	<0.01	0.005	<1	0.003	0.02	0.001
20. 0.035	<0.01	0.006	<1	0.004	0.017	0.001
21. 0.01	<0.01	0.007	<1	0.002	0.007	0.003
22. 7.66	<0.01	1.45	6	0.012	0.092	0.055
23. 1.93	<0.01	0.19	4	0.018	0.029	0.012
24. 0.07	<0.01	0.075	3	0.088	0.032	0.010
25. 0.095	<0.01	0.023	2	0.004	0.04	0.009
26. 2.10	<0.01	0.035	3	0.010	0.052	0.005
1-47	0.03	0.23	21	= Average grades		

Nº 1 WORKINGS




%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
1. 0.10	<0.01	0.20	1	0.005	0.009	0.005
2. 0.32	<0.01	0.95	5	0.017	0.096	0.024
3. 0.14	<0.01	3.50	7	0.025	0.36	0.016
4. 0.16	<0.01	4.10	7	0.017	0.26	0.024
5. 0.36	<0.01	0.57	2	0.01	0.028	0.022
6. 0.55	<0.01	1.40	3	0.009	0.052	0.006
0.27	<0.01	1.79	4	= Average grades		

Nº 4 WORKINGS




%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
1.U. 0.015	<0.01	0.29	<1	0.01	0.009	0.001
1.L. 0.11	<0.01	0.18	1	0.009	0.005	0.004
2. 0.015	<0.01	0.07	1	0.003	0.08	0.001
3. 2.01	0.053	0.031	29	0.033	0.12	0.042
4.U. 0.01	<0.01	0.06	<1	0.003	0.008	0.002
4.L. 0.015	<0.01	0.085	<1	0.001	0.019	0.001
5. 0.05	<0.01	0.45	1	0.008	0.01	0.003
6. 0.085	0.044	0.033	19	0.014	0.022	0.03
0.29	0.02	0.15	7	= Average grades		

Nº 5 WORKINGS




%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
1. 0.97	0.10	0.008	45	0.02	0.031	0.048
2.	N.A.					
3. 0.045	<0.01	0.26	1	0.003	0.008	0.003
4. 0.43	0.24	26.5	80	0.48	0.54	0.046
5. 3.56	0.044	0.15	60	0.019	0.13	0.055
6.	N.A.					
7. 180	0.096	0.016	90	0.035	0.05	0.22
1.36	0.10	5.39	55	= Average grades		

Nº 6 WORKINGS




%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
1. 0.54	0.60	23.0	220	0.95	0.56	0.50
2. 0.41	0.36	3.80	120	0.34	0.76	0.54
0.47	0.48	13.4	170	= Average grades		

Nº 7 WORKINGS



%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
1.	N.A.					
2. 0.76	0.26	0.008	90	0.018	0.048	0.24
3.	N.A.					
4. 1.52	1.03	0.05	420	0.25	0.09	0.53
5. 0.67	0.25	0.13	150	0.06	0.46	0.37
0.98	0.51	0.06	220	= Average grades		

Nº 8 WORKINGS




%Sn	%Sol.Sn	%Zn	g/t Ag	%Cu	%Pb	%As
2. 1.89	0.095	0.013	70	0.059	0.053	0.17
3. 1.28	0.12	0.011	15	0.019	0.046	0.065
1.58	0.11	0.01	42	= Average grade		

5 cm

%Sb	%As	%Pb	%Cu	%CaF ₂	%S	g/t Ag	%Zn	%Sol.Sn	%Sn
0.002	<0.10	0.005	<0.05	<0.10	0.06	<1	0.013	0.003	0.07
0.002	<0.10	0.004	<0.05	<0.10	0.12	1	0.009	<0.005	0.06
0.002	<0.10	0.001	<0.05	<0.10	0.09	2	0.010	<0.005	0.07
0.003	<0.10	0.003	<0.05	<0.10	0.18	2	0.015	0.008	0.07
0.003	<0.10	0.014	<0.05	<0.10	1.1	1	0.048	<0.005	0.07
0.003	<0.10	0.008	<0.05	<0.10	2.5	<1	0.031	<0.005	0.08
0.003	<0.10	0.015	<0.05	<0.10	4.1	<1	0.032	<0.003	0.17
0.003	<0.10	0.078	<0.05	<0.10	3.1	5	0.022	0.019	0.42
0.004	<0.10	0.50	<0.05	0.12	7.6	3	0.052	0.003	0.25
0.003	<0.10	0.026	<0.05	0.10	4.3	2	0.10	<0.005	0.30
0.004	<0.10	0.009	<0.05	<0.10	0.45	<1	0.037	<0.003	0.28
0.004	<0.10	0.34	<0.05	<0.10	3.7	4	0.34	0.015	0.48
0.004	<0.10	0.052	<0.05	0.16	4.7	3	1.50	0.006	3.01
0.011	<0.10	0.044	<0.05	0.32	6.6	1	0.14	0.003	1.85
0.002	<0.10	0.016	<0.05	<0.10	2.8	2	0.030	<0.005	0.83
0.002	<0.10	0.033	<0.05	<0.10	1.2	8	0.17	0.023	0.87
0.002	<0.10	0.010	<0.05	<0.10	0.62	<1	0.080	<0.005	0.19
0.004	<0.10	0.008	<0.05	<0.10	1.7	1	0.056	0.013	0.24
0.004	<0.10	0.022	<0.05	<0.10	1.6	3	0.40	0.013	3.32
0.006	<0.10	0.090	<0.05	<0.10	0.45	1	0.060	<0.003	0.20
0.004	<0.10	0.10	<0.05	<0.10	0.73	1	0.14	<0.003	0.18
0.010	<0.10	0.040	<0.05	<0.10	8.3	7	2.50	0.006	0.73
0.014	0.13	0.28	<0.05	<0.10	10.5	12	1.63	0.022	0.69
0.030	0.26	0.44	<0.05	<0.10	9	140	0.022	0.62	
0.58	0.43	0.16	<0.05	<0.10	6.1	13	1.10	0.015	0.45
0.078	<0.10	0.16	<0.05	0.14	11.1	9	1.70	0.017	0.68
0.10	<0.05	0.21	<0.05	0.20	9.8	10	1.10	0.009	0.61
0.19	0.11	0.40	<0.05	0.66	11.2	20	2.90	0.017	0.33
0.49	0.25	0.68	<0.05	0.94	7.1	25	2.20	0.044	0.60
0.50	0.26	0.30	<0.05	0.39	5.2	27	3.1	0.031	0.88
0.036	<0.10	0.116	0.06	0.68	10.0	22	3.60	0.046	0.59
<0.10	0.20	0.05				12	3.33	0.031	0.65

ADIT



%Sn	%Sol.Sn	%Zn	g/t Ag	%S	%CaF ₂	%Cu	%Pb	%As	%Sb
0.06	<0.005	0.010	<1	0.10	<0.10	<0.05	0.005	<0.10	0.001
0.06	<0.003	0.037	<1	0.08	<0.10	<0.05	0.005	<0.10	0.002
0.05	<0.005	0.017	<1	0.08	<0.10	<0.05	0.004	<0.10	0.003
0.06	<0.005	0.024	<1	0.16	<0.10	<0.05	0.004	<0.10	0.004
0.06	0.019	0.010	2	0.10	<0.10	<0.05	0.003	<0.10	0.002
0.07	0.015	0.019	2	0.52	<0.10	<0.05	0.020	<0.10	0.003
0.13	0.006	0.13	4	2.9	<0.10	<0.05	0.014	<0.10	0.004
0.18	0.006	0.085	6	4.3	<0.10	<0.05	0.030	<0.10	0.003
0.22	<0.005	0.26	2	7.5	<0.10	<0.05	0.046	<0.10	0.004
0.10	<0.003	0.072	1	3.3	<0.10	<0.05	0.009	<0.10	0.007
0.34		1	1.1	<0.10	<0.05		<0.10	0.004	
1.11	<0.005	0.580	1	1.0	<0.10	<0.05	0.022	<0.10	0.003
1.33	0.011	0.42	2	4.2	0.16	<0.05	0.030	<0.10	0.007
1.50	0.013	0.37	3	3.4	<0.10	<0.05	0.019	<0.05	0.003
1.19	<0.005	0.012	2		<0.05	0.009	<0.10		
0.08	<0.005	0.018	<1		<0.05	0.003	<0.05		
0.07	<0.005	0.085	4	1.8	<0.10	<0.05	0.12	<0.10	0.004
0.08	<0.003	0.28	1	0.57	<0.10	<0.05	0.021	<0.10	0.003
0.33	<0.005	0.670	2	2.8	<0.10	<0.05	0.011	<0.10	0.004
0.10	<0.003	0.038	1	0.34	<0.10	<0.05	0.018	<0.10	0.006
0.16	<0.005	0.056	2	0.68	<0.10	<0.05	0.022	<0.10	0.010
0.23	<0.005	0.032	2	5.1	<0.10	<0.05	0.046	<0.10	0.017
0.42	0.011	2.05	9	9.6	<0.10	<0.05	0.11	<0.10	0.015
0.61	0.017	1.92	8	10.1	<0.10	<0.05	0.290	0.10	0.011
0.22	0.018	2.17	9	9.0	0.27	<0.05	0.52	0.15	0.012
0.58	0.006	0.85	14	9.8	0.34	<0.05	0.60	<0.10	0.042
0.28	0.015	1.92	9	12.7	0.34	<0.05	0.35	0.40	0.018
0.28	0.022	1.67	22			<0.05	1.23	0.54	
0.52	0.018	2.50	14			<0.05	0.63	0.19	
0.47	0.028	2.67	25			<0.05	0.43	0.14	
0.63	0.046	4.17	20			<0.05	0.45	0.14	
0.67	0.012	0.042	2			<0.05	0.024	<0.10	
0.06	<0.005	0.045	<1			<0.05	0.012	<0.10	
0.08	<0.005	0.018	1			<0.05	0.030	<0.10	
0.89	<0.005	0.032	<1			<0.05	0.012	<0.10	